

	AP-5 PG 64-22		1621		2023-11-28 17:08
	520D120		RT2316214527		2023-11-26 09:00

, @15 kg/m ³	KSM 2002	1000	1045		
(15) cm	KSM 2254	100	140+		
,COC	KSM 2010	260	348		
FOAM ON HEAT,180	KSM 2201	NONE	NONE		
Loss on Heating wt%	KSM 2258	0.6	0.0		
가 ((%)) %	KSM 2252	55	62		
%	KSM 2252	110	108		
(25)	KSM 2252	50 ~ 80	74		
가 mass%	KSM 2202-2	99.0	99.9		
	KSM 2250	44.0 ~ 52.0	47.5		
@120 mm ² /s	ASTM D4402	To be reported	964.5		
@135 mm ² /s	ASTM D4402		443.8		
@150 mm ² /s	ASTM D4402	To be reported	228.0		
@180 mm ² /s	ASTM D4402	To be reported	77.9		
PG- (7)	KSF 2389	64	64		
PG-	KSF 2389	-22	-22		

K. W. Hwang

