

	AP-5 PG 64-22	1621		2023-03-10 17:24
	520D122	RT2316214401		2023-03-07 13:00

, @15 kg/m <sup>3</sup>	KSM 2002	1000	1038	
(15 ) cm	KSM 2254	100	140+	
,COC	KSM 2010	260	330	
FOAM ON HEAT,180	KSM 2201	NONE	NONE	
Loss on Heating wt%	KSM 2258	0.6	0.0	
가 ( ( % ) ) %	KSM 2252	55	66	
%	KSM 2252	110	106	
(25 )	KSM 2252	60 ~ 80	71	
가 mass%	KSM 2202-2	99.0	99.9	
	KSM 2250	44.0 ~ 52.0	48.0	
@120 mm <sup>2</sup> /s	ASTM D4402	To be reported	979.7	
@135 mm <sup>2</sup> /s	ASTM D4402		441.5	
@150 mm <sup>2</sup> /s	ASTM D4402	To be reported	223.3	
@180 mm <sup>2</sup> /s	ASTM D4402	To be reported	74.7	
PG- (7 )	KSF 2389	64	64	
PG-	KSF 2389	-22	-22	

*K. W. Hwang*
