

	AP-5 PG 64-22	1621		2023-08-16 08:57
	520D122	RT2316214478		2023-08-11 04:00

, @15 kg/m ³	KSM 2002	1000	1039	
(15) cm	KSM 2254	100	140+	
,COC	KSM 2010	260	360	
FOAM ON HEAT,180	KSM 2201	NONE	NONE	
Loss on Heating wt%	KSM 2258	0.6	0.0	
가 ((%)) %	KSM 2252	55	71	
%	KSM 2252	110	103	
(25)	KSM 2252	60 ~ 80	68	
가 mass%	KSM 2202-2	99.0	99.9	
	KSM 2250	44.0 ~ 52.0	48.0	
@120 mm ² /s	ASTM D4402	To be reported	988.6	
@135 mm ² /s	ASTM D4402		448.7	
@150 mm ² /s	ASTM D4402	To be reported	228.1	
@180 mm ² /s	ASTM D4402	To be reported	76.8	
PG- (7)	KSF 2389	64	64	
PG-	KSF 2389	-22		

K. W. Hwang

