

	AP-5 PG 64-22		1621		2026-06-09 08:20
	620D504		RT2616214807		2026-06-05 03:00

, @15 kg/m ³	KSM 2002	1000	1036	
(15) cm	KSM 2254	100	140+	
,COC	KSM 2010	260	356	
FOAM ON HEAT,180	KSM 2201	NONE	NONE	
Loss on Heating wt%	KSM 2258	0.6	0.0	
가 ((%)) %	KSM 2252	55	71	
%	KSM 2252	110	106	
(25)	KSM 2252	50 ~ 80	62	
가 mass%	KSM 2201	99.0	99.9	
	KSM 2250	44.0 ~ 52.0	47.0	
@120 mm ² /s	ASTM D4402	To be reported	991.7	
@135 mm ² /s	ASTM D4402		441.2	
@150 mm ² /s	ASTM D4402	To be reported	221.0	
@180 mm ² /s	ASTM D4402	To be reported	73.0	
PG- (7)	KSF 2389	64	64	
PG-	KSF 2389	-22	-22	
at 64 G*/sinδ)	KSF 2389		1.07	
가 at 64 G*/sinδ)	KSF 2389		2.26	
at 25 (G*.sinδ)	KSF 2389		3041	
m at -12	KS F 2390		0.314	
at -12	KS F 2390		143.9	

최명수

